



THE BLACK VAULT

This document was obtained from The Black Vault, an online database of declassified government documents. This particular record is housed in the MKULTRA/Mind Control Collection, a compilation of more than 20,000 pages declassified by the Central Intelligence Agency (CIA).

The entire collection is free to download and online at:

<http://mkultra.theblackvault.com>

Identity

Poly methyl Methacrylate

A/B, 7, 5/12

Source

Indefinite

Age

Indefinite

Notes

Identity established by

C

Polymethyl methacrylate with the possibility of a few percent of cross linked esters in addition to polymethylmethacrylate.

Identification was made on basis of

- (1) infra red spectrum (submitted with this report,
- (2) elemental analysis C 60.53% H 7.93%
- (3) density 1.19 @ 25°C.
- (4) softening point ca. 130°C.
- and (5) solubility in sulfuric acid and ethyl acetate.

Source This resin is produced in U.S. Work

has been done on it in many foreign countries

H-B/3
[redacted] has raw materials from other processes (by-products) which make it more economical to manufacture than in [redacted] where work has been done on the substance.

The casting resembles products made in [redacted]. Several subjective opinions were rendered to the effect that its composition and appearance might lead one to believe that this was its origin.